

MIXING DATA SHEET

EPOXIES

TYPE	COLOUR	NOTES	MIX RATIO						RATIO [%]			
			DENSITY		WEIGHT		VOLUME		WEIGHT		VOLUME	
			A	B	A	B	A	B	A	B	A	B
EPOXY WITH SLEEVE		APPLICABLE PRODUCTS										
S1239	BLACK	HTLP60 / DIRAX / RAYTRANS	1,39	0,93	100	40,00	1,73	1	71	29	63	37
S1301-M	BLACK	HTLP60 / DIRAX / HTLP60-HP / HTLP80	1,65	1,00	100	19,90	3,00	1	83	17	75	25
S1401	GRAY	PPS120 / PP-REPAIR	1,8	1,09	100	12,00	5,00	1	89	11	83	17
STAND ALONE EPOXY		MAXIMUM OPERATING TEMPERATURE										
R60	BROWN	MAX. 60°C	1,75	0,98	100	14,70	3,8	1	87	13	79	21
R95	GRAY	95°C	1,78	1,03	100	16,00	3,60	1	86	14	78	22
R120	GRAY	120°C	1,78	1,03	100	16,00	3,60	1	86	14	78	22
PC-PW	BEIGE	50°C	1,84	0,98	100	5,50	9,75	1	95	5	91	9

BERRY PLASTICS PROPRIETARY INFORMATION